

ul. Harcerska 8, 18-100 Łapy, tel. 085 715 33 28, fax 085 715 76 81 PKO BP S.A. 96 1020 1332 0000 1502 0324 0447 NIP: 966-176-77-14, REGON: 200133730 www.termopasty.pl, e-mail: biuro@termopasty.pl

Product Data Sheet

Heat conductive silicone paste

It facilitates heat transfer between the electronic components and radiator. It is necessary for correct operation of any type of temperature sensors. It protects from weather conditions and prevents from breakthrough. It is characterized by very good chemical resistance for oxidation, water solutions of acids, alkalis and salts, sulphur dioxide and ammonia. It has a very wide range of work temperatures.



Properties:

- Density at. 20°C: 1,47 g/cm³
- Flash point: 350°C
- Freezing point: -50°C
- Refraction coefficient: 1,405
- Specific heat at 50°C: 0,243 Cal /g K
- Overall heat-transfer coefficient at 0-50°C:0,88 W/m K,
- Dielectric constant at 100 Hz: 4,7 (±0,1)
 - Cross-through resistance: 5 x 10¹⁴ Ohm x cm
- Loss tangent at $f = 100 \text{ Hz}: 0,020 (\pm 0,003)$,
 - Operating temperature range: -50~200°C

Package:

Weight	Package	Symbol
7 g (metal tube)	10	AGT-055
25 g (syringe)	2 or 16	AGT-056
100 g (jar)	6 or 36	AGT-057
1000 g (jar)	1	AGT-058
5000 g (pail)	1	AGT-059

